

## **S.247 – SPECIFICATION: REFLECTOR™ Enhancer Flooring System (Standard Performance)**

CSI Division 09 – Finishes: 096566, 096700, 099600

Revised: 7.20.11

### **Part 1 – GENERAL**

#### **1.1 RELATED DOCUMENTS**

- A. Drawings and general provisions of the contract, including General and Supplementary Conditions and Division 1 Specifications Sections, apply to this Section.

#### **1.2 SUMMARY**

- A. This section includes resinous flooring systems with epoxy and REFLECTOR™ Enhancer.
  - 1. Application method: Epoxy flooring with integral REFLECTOR™ Enhancer as shown on the drawings and in schedules.
- B. Related sections include the following:
  - 1. Cast-in-Place Concrete (Section 03300)
  - 2. See Paragraph 1.7 B Condition of New Concrete

#### **1.3 SYSTEM DESCRIPTION**

- A. The work shall consist of preparation of the substrate, the furnishing and application of a 100% solids pigmented epoxy floor base coating, 100% solids clear epoxy topcoat with integral REFLECTOR™ Enhancer in chosen color(s) and optional VOC compliant urethane protective topcoat. The system shall have the color and texture as specified by the Owner. It shall be applied to the properly prepared area (s) as defined in the plans strictly in accordance with the Elite Crete Systems recommendations.

#### **1.4 SUBMITTALS**

- A. Product Data: Insert the manufacturers Product literature including installation procedures.
- B. Manufacturers Material Safety Data Sheet (MSDS)
- C. Samples: A 12” square sample of the proposed system including a representative thickness with Owners desired texture and finish.

#### **1.5 QUALITY ASSURANCE**

- A. The Manufacturer shall have a minimum of 10 years experience in the production, sales and technical support of epoxy industrial flooring and related materials.
- B. The Applicator shall have been approved and certified by the flooring system manufacturer in all phases of surface preparation and application of the product specified.
- C. No requests for substitutions shall be considered that would change the generic type of the system specified.
- D. The specified system shall be in compliance with the requirements of the United States Department of Agriculture (USDA).

- E. A pre-installation conference shall be held between the Applicator, General Contractor and the Owner to review and clarify this specification, application procedure, quality control, inspection and acceptance criteria and production schedule.

## 1.6 PRODUCT DELIVERY AND STORAGE

- A. Packing and Shipping
- B. All components of the system shall be delivered to the site in the manufacturers packaging, clearly identified with the product type and batch number.
- C. Storage and Protection
- D. The Applicator shall be provided with a storage area for all components and related materials. The storage area shall be between 60 F and maximum of 90 F, dry and out of direct sunlight in accordance with Elite Crete Systems recommendations and relevant health and safety regulations.
- E. Copies of the Material Safety Data Sheet (MSDS) for all components shall be kept on site for review by all personnel involved in the project.
- F. Waste Disposal
  - 1. The applicator shall be provided with adequate waste disposal facilities for non-hazardous waste generated during the installation of the system.

## 1.7 PROJECT CONDITIONS

- A. Site Requirements
  - 1. Application shall proceed when air, material and substrate temperatures are between 60 F and 90 F, providing the substrate temperature is above the dew point. If this condition cannot be met, contact Elite Crete Systems for recommendations.
  - 2. The relative humidity shall be less than 85% and the surface temperature shall be at least 5 degrees above the dew point.
  - 3. The Applicator shall ensure that the adequate ventilation is available for the work area.
  - 4. The applicator shall be supplied with adequate lightning during the preparation and installation process.
- B. Conditions of New Concrete to be coated with the Elite Crete Systems REFLECTOR™ Enhancer flooring.
  - 1. The concrete shall be moisture cured for a minimum of 7 days and have fully cured a minimum of 28 days in accordance with ACI-308 standard, prior to the application of the coating system pending moisture tests.
  - 2. New concrete shall have a flat rubbed finish or at most a light steel trowel finish, (a hard steel trowel finish is not desirable).
  - 3. Cure and seal agents for concrete should not be used.
  - 4. All concrete surfaces on grade shall be constructed with a working vapor barrier under the slab to protect against the effects of vapor transmission and possible delamination of the system.
- C. Safety requirements
  - 1. Non-related personnel in the work area shall be kept to a minimum.
  - 2. The Owner shall be responsible to keep all traffic off the work area during the application and cure of the system.

## 1.8 WARRANTY

- A. Elite Crete Systems warrants that the material shipped to the buyers at the time of shipment shall be free from manufacturing defects and perform to Elite Crete Systems published literature if used in accordance with Elite Crete Systems prescribed procedures.
- B. Elite Crete Systems total liability with respect to this warrantee is strictly limited to the value of the material purchase.

## PART 2- PRODUCTS

### 2.1 FLOORING

- A. Elite Crete Systems products used for the REFLECTOR™ Enhancer Flooring Systems.
  - 1. System Materials
    - a. Primer – E100-VB5™ Epoxy Vapor barrier (if determined as needed during testing)
    - b. Base coat – E100-PT4™ Standard or Fast Set Pigmented Epoxy
    - c. REFLECTOR™ Enhancer in - E100-PT1™ Standard or Fast Set or E100-UV1™
    - d. Protective (optional but recommended): AUS-V™ gloss or satin

### 2.2 MANUFACTURER

- A. Elite Crete Systems, Inc., 1061 Transport Drive, Valparaiso, IN 46383 USA  
 Phone: 1+219-465-7671, FAX: 1+219-531-0898
- B. Manufacturer of approved system shall be single source and made in the USA.

### 2.3 PRODUCT REQUIREMENTS

<ul style="list-style-type: none"> <li>A. Primer                             <ul style="list-style-type: none"> <li>1. Percent solids</li> <li>2. VOC</li> <li>3. Bond Strength ASTM D 4541</li> <li>4. Hardness ASTM 2370</li> </ul> </li> </ul>	<p>E100-VB5™ Epoxy Vapor Barrier</p> <p>58% solids</p> <p>0%</p> <p>Substrate failure &gt; 450 psi)</p> <p>n/a</p>
<ul style="list-style-type: none"> <li>B. Base Coat                             <ul style="list-style-type: none"> <li>1. Percent solids</li> <li>2. VOC</li> <li>3. Compressive Strength ASTM D 645</li> <li>4. Tensile Strength ASTM D 638</li> <li>5. Flexural Strength ASTM D 790</li> <li>6. Shore D Hardness ASTM D 2240</li> </ul> </li> </ul>	<p>E100-PT4™ Pigmented Epoxy</p> <p>100%</p> <p>0%</p> <p>9,500 psi</p> <p>7,700 psi</p> <p>4,500 psi</p> <p>83 (7 days)</p>
<ul style="list-style-type: none"> <li>C. REFLECTOR™ Enhancer Color Coat                             <ul style="list-style-type: none"> <li>1. Percent solids</li> <li>2. VOC</li> <li>3. Compressive Strength ASTM D 645</li> <li>4. Tensile Strength ASTM D 638</li> <li>5. Abrasion Resistance ASTM 4060                                      CS-Wheel, 1 kg load</li> <li>6. Flexural Strength ASTM D 790</li> <li>7. Shore D Hardness ASTM D 2240</li> </ul> </li> </ul>	<p>E100-PT1™ or E100-UV1™ Epoxy</p> <p>100%</p> <p>0%</p> <p>12,000 psi</p> <p>7,100 psi</p> <p>30 mg loss</p> <p>7,500 psi</p> <p>89 (7 days)</p>
<ul style="list-style-type: none"> <li>D. Protective Coat                             <ul style="list-style-type: none"> <li>1. Percent Solids</li> <li>2. VOC</li> <li>3. Abrasion Resistance                                      CS-Wheel, 1 kg load @ 500 cycles</li> <li>4. Flexibility</li> <li>5. Adhesion to E100-UV1 ASTM 4541</li> <li>6. Water Spot resistance</li> <li>6. Blush resistance</li> </ul> </li> </ul>	<p>AUS-V™</p> <p>75%</p> <p>25 g/l (mixed)</p> <p>17 mg loss</p> <p>No crack or defects on 1/8" mandrel</p> <p>Substrate failure &gt; 450 psi</p> <p>No water spotting</p> <p>Blush resistant</p>

## PART 3 – SUBSTRATE EXAMINATION

### 3.1 Examination

- A. Applicator and Owner or his representative examine substrates, areas and conditions for compliance with requirements for maximum moisture content (7%) by means of calcium chloride test or vapor test. Review installation tolerances or other factors that may affect flooring performance.
- B. Verify that the substrate(s) and conditions are satisfactory for flooring installation and comply with manufacturers requirements for a successful installation.

### 3.2 PREPARATION

- A. General
  - 1. New and Existing concrete surfaces shall be free from oil, grease, curing compounds, weak or deteriorated concrete, all laitance and other foreign matter that may affect bond including bituminous products.
  - 2. Moisture testing: Perform anhydrous calcium chloride test ASTM F 1869-98, first three tests in the first 1000 sq. ft. and 1 test for every 1000 sq. ft. after that.
    - 2a. The successful test result is the concrete will not have a vapor drive exceeding 3 lbs./1000 sq. ft./24 hours.
    - 2b. If the vapor drive exceeds 3 lbs. in 24 hours, then the owner and or his engineer shall be notified and advised of additional cost to install a vapor mitigation system that has been approved by the manufacturer or other means to lower to an acceptable limit.
- B. There shall be no standing water or moisture visible on the surface at time of application.
  - 1. Mechanical Surface Preparation
    - 1a. Mechanically prepare (grind or shot blast) the surface removing the laitance to achieve a sound hard surface to receive the primer and or coating.
    - 1b. Edges and other surfaces that cannot be reached by shot blasting, use a mechanical grinder, or other abraded.
    - 1c. The finished profile shall have all paint, other toppings and hardened concrete, including a burnished power troweled smooth surface REMOVED. The finished profile shall conform to the International Concrete Repair Institute (ICRI) CSP-3 profile or better.
    - 1d. All terminations at doorways or around drains shall have a ¼" x ¼" cut known as a 'key' to provide a smooth professional transition.
    - 1e. Non moving cracks shall be chiseled out and filled according to manufacturer's recommendations.
    - 1f. All moving cracks and Joints shall be filled according to manufacturer's recommendation's.
    - 1g. All spalled or worn areas shall be chipped out and repaired according to the manufacturer's recommendations.

### 3.3 APPLICATION

- 1. General: Apply components of resinous flooring system according to manufacturer's written instructions to provide a uniform, monolithic wearing surface of thickness indicated. Finished floor thickness to be 35 to 40 mils.
- A. Primer (Vapor Barrier Epoxy - if determined as needed during testing)
  - 1. Mix primer according to the manufacturer's instructions.
  - 2. The primer shall be applied by flat squeegee and back roll with a non linting roller at 200-250 sq. ft. per gallon to yield a dry film thickness not to exceed 4-5 mils. Allow to cure.
- B. Base Coat
  - 1. Mix coating according to manufacturer's instructions
  - 2. Apply first coat with flat squeegee @ 100 to 125 sq. ft per gallon and back roll with a non linting roller per gallon.
- C. REFLECTOR™ Enhancer Coat
  - 1. Mix clear epoxy according to the manufacturer's instructions.

2. Add chosen color(s) of REFLECTOR™ Enhancer to mixed clear epoxy and apply in method to create approved appearance and allow to cure.

D. Protective Coat (optional but recommended)

1. Mix protective coat according to manufacturer's instructions and add AUS-V™ AGG according to manufacturer's instructions to achieve the chosen satin to matt finish if desired.
2. Apply protective coat with a non-linting roller @ 500-550 square feet per gallon and back roll with a non linting roller. Allow to cure.
3. Allow to cure 12-24 hours depending upon temperature before opening to all traffic.

### 3.4 CLEAN UP

- A. remove masking tape and all rubbish from area, clean any over sprayed material.