

## TD.490 – TECHNICAL DATA: Powdered Accelerator

Revised: 8.14.08

Product Name: Powdered Accelerator

Product Class: Dry, Cement based product

### Description:

A highly concentrated, cement based and cement compatible powdered accelerator for cementitious polymer modified overlays. Recommended use is 8 to 24 ounces per bag of TEXTURE-PAVE™ or THIN-FINISH™ Overlay or 5 gallons of mixed polymer overlay material.

Set time will vary depending on ambient temperature, surface temperature, humidity, material color and water temperature. User should experiment with powdered accelerator prior to use to determine exact increased set time.

Powdered accelerator is not recommended for exterior use in direct sunlight when the ambient temperature is above 70° F.

### Use Applications:

- For increasing the set time of THIN-FINISH™, TEXTURE-PAVE™ or MICRO-FINISH™.

### Key Features:

- Accelerates the cure time without the affects of calcium chloride based accelerators.
- Will not cause matrix deterioration as calcium chloride accelerators would.

### Product Properties:

- Appearance – Fine White Powder
- Smell – N/A
- Nonvolatile Content % - N/A
- GT Temperature – N/A
- Flammability - N/A
- Weight, Lb. Per stock container – 45 pounds.
- Application temperature - 40° - 80° F
- Cured – N/A

### Available Packaging:

- Stock – 45 pound pails
- Special Order - Inquire

### Suggested Storage:

- Keep Dry
- Shelf Life - 6 months to a year

DOT Classification: Mortar, Not Regulated, Non-Hazardous, Class 50