

**TD.485 – TECHNICAL DATA: Performance for HERMETIC™ Color Quartz or Stout Floor**

Revised: 1.18.16

**Product Name:** HERMETIC™ Color Quartz or Stout Floor

**Description:**

A fluid applied in place, resinous, seamless flooring system where colored quartz aggregate or natural silica quartz is broadcasted or troweled into the resin. These flooring systems are top coated with either clear or pigmented resins.

The follow products can be used as aggregate binder: E100-PT4™, E100-PT1™, E100-UV1™ or E100-VR1™ broadcast or trowel applied flooring systems.

**USES:**

- |                       |              |                   |
|-----------------------|--------------|-------------------|
| Classrooms            | Laboratories | Corridors         |
| Bathrooms             | Cafeterias   | Industrial plants |
| Pharmaceutical plants | Showrooms    | Foyers            |

**FEATURES:**

- Easy to maintain
- Chemical resistant
- Superior wear for longevity
- Decorative

<b>Property</b>	<b>Physical Properties Test Standard</b>	<b>Result</b>
Mix Ratio:		2 to 1 by volume for binder
Gel Time:	ASTM C-881	15-25 minutes
Colors:		as selected by the owners representative
Compressive strength	ASTM D-695	9,500 - 18,000 psi
Tensile strength	ASTM D-638	2,100 - 4,100 psi
Flexural strength	ASTM D790	4,500 - 6,300 psi
Concrete bond strength	ACI-403	350 psi substrate fails
Water absorption (2 hour boil)	ASTM D-570	0.03%
Slip resistance	ASTM F 609	0.5 minimum
Coefficient of friction	ASTM D 2047	0.5
Indentation	Mil D 3134 F	0.025 max
Impact resistance	Mil D 3134 F	16.5ft. lbs Pass
Flammability	ASTM D 570	Self extinguishing
Flame spread - NFPA 101	ASTM E-84	Class A
Hardness: Shore D	ASTM D 2240	75-83
CoE (thermal expansion)	ASTM D 696	0.2 X 10 <sup>6</sup> TH
VOC		0% VOC