

TD.402 – CHEMICAL RESISTANCE: SPARTIC-ALL™ RM

Revised: 3/16/2023 Version: 1.2

SPARTIC-ALL™			
Chemical Resistance			
Spot test at 70° F / 21° C			
	1 Hour	4 Hours	24 Hours
Water	No Effect	No Effect	No Effect
Iso-propyl alcohol	No Effect	No Effect	No Effect
Gasoline	No Effect	No Effect	No Effect
Motor oil	No Effect	No Effect	No Effect
Transmission fluid	No Effect	No Effect	No Effect
Anti-freeze	No Effect	No Effect	No Effect
Skydrol	No Effect	Softened Stain	Softened Stain
Ammonia Hydroxide (14%)	No Effect	No Effect	No Effect
Sulfuric Acid (50%)	No Effect	No Effect	No Effect
Bleach (50%)	No Effect	No Effect	No Effect
Betadine	No Effect	Light Stain	Stain
Brake fluid	No Effect	Softened Light Stain	Softened Stain

Hot Tire Staining (Pirelli)		
140° F / 60° C for 2 hr, 1 hr at 250 psi		
	Dry	Wet
Initial stain, 1 to 5 rating, 5 = not present	4	4
Stain cleaned, 1 to 5 rating	5	4
Initial imprint, 1 to 5 rating, 5 = not present	4	4
Imprint cleaned, 1 to 5 rating	4	4