

1151 Transport Drive Valparaiso, IN 46383 Toll Free 888.323.4445 • P 219.465.7671 elitecrete.com

TD.449 – TECHNICAL DATA: CXS-37R™ Clear Sealer

Revised: 3/16/2023 Version: 1.3

## **Product Description:**

CXS-37R<sup>™</sup> is a waterborne, thin film build sealer which is NMP/NEP free, and is designed to give a gloss finish with high abrasion resistance. Based on state of the art, self-crosslinking technology that cures as the wet film dries.

## Features:

- NMP and NEP free, complies with European regulatory requirements
- Meets current US, Canadian, and EU VOC regulations
- Excellent wear properties and chemical resistance
- Adhesion to multiple substrates
- Interior floor sealer designed for cementitious overlays and concrete substrates

Physical Properties		
@73° F / 23° C, 50% R.H.		
Taber abrasion	19mg loss	
Appearance	Translucent to slightly cloudy dispersion	
Total solids by weight %	37.0 ± 1.0	
Total solids by volume %	36.7 ± 1.0	
Density	8.69 (1.04) lbs/gal (g/ml)	
Brookfield viscosity	<100 cps	
pH	8.0-9.0	
Volatile organic content	2.5 wt % (<50 g/L)	
MFFT	<4.4 °C	
Freeze-thaw stability	Protect from freezing	

# Coverage rate:

• Two coat application required at a coverage of 250 ft<sup>2</sup> / 1 gallon (23.23 m<sup>2</sup> / 3.78 liters)

# **Suggested Storage:**

- Store in a temperature and weather-controlled area between 65° F / 18° C and 85° F / 29° C.
- Do not allow to freeze.
- Shelf Life: 1 year in original unopened containers.

### Available packaging:

• 1 gal, 5 gal, or 55 gal drums (special order only)

The information herein is general information to assist our cusbmers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products for. Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability of titness for a particular purpose, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and inno event shall we be liable for incidental or consequential damages.