# HERMETIC™ Paramount

Flooring System















Engineered High Performance Surfaces & Flooring

## HERMETIC™ Paramount Flooring Systems

are high build, self leveling, resinous slurry flooring system engineered for industrial applications. Available in either solid pigment or colored guartz for a speckled finish.

#### TYPICAL AREAS OF USE

- Warehouses
- Manufacturing areas
- · Laboratories & clean rooms
- Automotive service areas & garages
- Hospitals
- Schools
- Airports
- · Shopping malls

#### **ADVANTAGES**

- · Ease of maintenance
- Aesthetic improvements
- Increases the strength of the substrate
- · Hard and abrasion resistant
- VOC free CA 01350 air quality compliant
- · Stain and chemical resistant
- Antimicrobial
- Fast set available for quicker turnaround time

#### **SPECIFICATION OVERVIEW**

- Name: HERMETIC™ Paramount Floor
- Cured Thickness: @ 125 to 135 mils
- Surface preparation and detailed application instructions per manufacturer
- Manufacturer: Elite Crete Systems, Inc. +1-219-465-7671

#### SAMPLE COLOR CHART




**NOTE:** The colors depicted on this technical document may not illustrate the exact color. Contact a technical support representative for a more accurate color sample. Custom colors availible upon request.

\* Novalac Only

### **PHYSICAL PROPERTIES**

(@ 73°F / 23°C, 7 day ambient cure as a coating)

PROPERTY	TEST	RESULT
VOC Content	N/A	0 g/l
Shore D Hardness	ASTM D-2240	90+
Water Absorption (2hr boil)	ASTM D-570	0.09 %
Toxicity	N/A	None*
Heat Distortion Temperature	ASTM D-648	128 F / 51 C
Compressive Strength	ASTM D-695	14,400 psi minimum
Tensile Strength	ASTM D-638	4,100 psi
Flexural Strength	ASTM D-790	4,200 psi
Abrasion Resistance **	ASTM D-4060	0.5 mg loss
Slant Shear	ASTM C-882	100% concrete failure
Flammability	ASTM D-635	Self-extinguishing
Flame Spread Rate (NFPA 101)	ASTM E-84	Class A
Elongation at Break	ASTM D-638	4.1 %
Chemical Resistance	Contact technical representative for chart	
Coefficient of Friction	Adjusted per requirement. Generally 0.80+	
COF Guidelines:	ADA Flat Surfaces	0.60
	ADA Inclined Surface	es 0.80
	OSHA	0.50
	NFPA	0.68
* FDA LICDA O CIEA A	** CC 17 Wheel 1 VC lead 1 000 and a	





## elite crete systems

#### Elite Crete Systems, Inc.

1151 Transport Drive Valparaiso, Indiana 46383

Phone: +1.219.465.7671 Fax: +1.219.531.0898

Toll Free: 888-323-4445 Email: info@elitecrete.com

### www.elitecrete.com

The information herein is general information to assist our customers in determining whether our products are suitable for their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers should inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products for. Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose, nor is replacement of our materials and in no event shall we be liable for incidental or consequential damages.